Materials for Civil and Construction Engineers 4th edition Mamlouk Solutions Manual

SKU: 9780134320533-SOLUTIONS

CHAPTER 2. NATURE OF MATERIALS

2.1. See Section 2.2.1.

2.2. See Section 2.1.

2.3. See Section 2.1.1.

2.4. See Section 2.1.1.

2.5. See Section 2.1.2.

2.6. See Section 2.2.1.

2.7. See Section 2.1.2.

2.8. See Section 2.2.1.

2.9. See Section 2.2.1.

2.10. If the atomic masses and radii are the same, then the material that crystalizes into a lattice with a higher APF will have a larger density. The FCC structure has a higher APF than the BCC structure.

This work is protected by United States copyright laws and is provided solely for the use of instructors in teaching their courses and assessing student learning. Dissemination or sale of any part of this work (including on the World Wide Web) will destroy the integrity of the work and is not permitted.

2.11. For the face-center cubic crystal structure, number of equivalent whole atoms in each unit cell = 4

By inspection the diagonal of the face of a FCC unit cell = 4r

Using Pythagorean theory:

$(4r)^2 = a^2 + a^2$

$16r^2 = 2\,a^2$

$8r^2 = a^2$

$a = 2\sqrt{2}r$

2.12. a. Number of equivalent whole atoms in each unit cell in the BCC lattice structure = **2**

b. Volume of the sphere = $(4/3)\,\pi\,r^3$

Volume of atoms in the unit cell = $2 \times (4/3)\,\pi\,r^3 = (8/3)\,\pi\,r^3$

By inspection, the diagonal of the cube of a BCC unit cell

$= 4r = \sqrt{a^2 + a^2 + a^2} = a\sqrt{3}$

a = Length of each side of the unit cell = $\dfrac{4r}{\sqrt{3}}$

© 2017 Pearson Education, Inc., Hoboken, NJ. All rights reserved. This material is protected under all copyright laws as they currently exist. No portion of this material may be reproduced, in any form or by any means, without permission in writing from the publisher.

Materials for Civil and Construction Engineers 4th edition Mamlouk Solutions Manual

c. Volume of the unit cell = $\left[\frac{4r}{\sqrt{3}}\right]^3$

$$APF = \frac{volume\ \ of\ \ atoms\ \ in\ \ the\ \ unit\ \ cell}{total\ \ unit\ \ volume\ \ of\ \ the\ \ cell} = \frac{(8/3)\pi.r^3}{(4r/\sqrt{3})^3} = \mathbf{0.68}$$

2.13. For the BCC lattice structure: $a = \frac{4r}{\sqrt{3}}$

Volume of the unit cell of iron = $\left[\frac{4r}{\sqrt{3}}\right]^3 = \left[\frac{4x0.124x10^{-9}}{\sqrt{3}}\right]^3$ = **2.348 x 10^{-29} m^3**

2.14. For the FCC lattice structure: $a = 2\sqrt{2}r$

Vol. of unit cell of aluminum = $(2\sqrt{2}r)^3 = (2\sqrt{2}x0.143)^3 = 0.06616725\ nm^3$ = **6.6167x10^{-29} m^3**

2.15. From Table 2.3, copper has an FCC lattice structure and r of 0.1278 nm

Volume of the unit cell of copper = $(2\sqrt{2}r)^3 = (2\sqrt{2}x0.1278)^3$ = **0.04723 nm^3 = 4.723 x10^{-29} m^3**

2.16. For the BCC lattice structure: $a = \frac{4r}{\sqrt{3}}$

Volume of the unit cell of iron = $\left[\frac{4r}{\sqrt{3}}\right]^3 = \left[\frac{4x0.124x10^{-9}}{\sqrt{3}}\right]^3$ = 2.348 x 10^{-29} m^3

Density = $\rho = \frac{nA}{V_C N_A}$

n = Number of equivalent atoms in the unit cell = 2

A = Atomic mass of the element = 55.9 g/mole

N_A= Avogadro's number = 6.023 x 10^{23}

$\rho = \frac{2x55.9}{2.348x10^{-29}x6.023x10^{23}}$ = 7.904 x 10^6 g/m^3 = **7.904 Mg/m^3**

2.17. For the BCC lattice structure: $a = \frac{4r}{\sqrt{3}}$

Vol. of the unit cell of molybdenum = $\left[\frac{4r}{\sqrt{3}}\right]^3 = \left[\frac{4x0.1363x10^{-9}}{\sqrt{3}}\right]^3$ = 3.119 x 10^{-29} m^3

$\rho = \frac{nA}{V_C N_A} = \frac{2x95.94}{3.119x10^{-29}x6.023x10^{23}}$ = 10.215 x 10^6 g/m^3= **10.215 Mg/ m^3**

© 2017 Pearson Education, Inc., Hoboken, NJ. All rights reserved. This material is protected under all copyright laws as they currently exist. No portion of this material may be reproduced, in any form or by any means, without permission in writing from the publisher.

Materials for Civil and Construction Engineers 4th edition Mamlouk Solutions Manual

2.18. For the BCC lattice structure: $a = \frac{4r}{\sqrt{3}}$

Volume of the unit cell of the metal = $\left[\frac{4r}{\sqrt{3}}\right]^3 = \left[\frac{4x0.128x10^{-9}}{\sqrt{3}}\right]^3$ = 2.583 x 10^{-29} m^3

$$\rho = \frac{nA}{V_C N_A} = \frac{2x63.5}{2.583x10^{-29}x6.023x10^{23}} = 8.163 \text{ x } 10^6 \text{ g/m}^3 = \mathbf{8.163\ Mg/\ m^3}$$

2.19. For the FCC lattice structure: $a = 2\sqrt{2}r$

Volume of unit cell of the metal = $(2\sqrt{2}r)^3 = (2\sqrt{2}x0.132)^3$ =0.05204 nm^3 = 5.204x10^{-29} m^3

$$\rho = \frac{nA}{V_C N_A} = \frac{4x42.9}{5.204x10^{-29}x6.023x10^{23}} = 5.475 \text{ x } 10^6 \text{ g/m}^3 = \mathbf{5.475\ Mg/\ m^3}$$

2.20. For the FCC lattice structure: $a = 2\sqrt{2}r$

Volume of unit cell of aluminum = $(2\sqrt{2}r)^3 = (2\sqrt{2}x0.143)^3$ =0.06616725 nm^3 = 6.6167x10^{-29} m^3

Density = $\rho = \frac{nA}{V_C N_A}$

For FCC lattice structure, n = 4

A = Atomic mass of the element = 26.98 g/mole

N_A= Avogadro's number = 6.023 x 10^{23}

$$\rho = \frac{4x26.98}{6.6167x10^{-29}x6.023x10^{23}} = 2.708 \text{ x } 10^6 \text{ g/m}^3 = \mathbf{2.708\ Mg/m^3}$$

2.21. $\rho = \frac{nA}{V_C N_A}$

For FCC lattice structure, n = 4

$V_c = \frac{4x63.55}{8.89x10^6 x6.023x10^{23}}$ = 4.747 x 10^{-29} m^3

APF = 0.74 = $\frac{4x(4/3)\pi.r^3}{4.747x10^{-29}}$

r^3 = 0.2097 x 10^{-29} m^3

r =0.128 x 10^{-9} m = **0.128 nm**

2.22. a. $\rho = \frac{nA}{V_C N_A}$

For FCC lattice structure, n = 4

$V_c = \frac{4x40.08}{1.55x10^6 x6.023x10^{23}}$ = 1.717 x 10^{-28} m^3

© 2017 Pearson Education, Inc., Hoboken, NJ. All rights reserved. This material is protected under all copyright laws as they currently exist. No portion of this material may be reproduced, in any form or by any means, without permission in writing from the publisher.

Materials for Civil and Construction Engineers 4th edition Mamlouk Solutions Manual

b. APF = 0.74 = $\frac{4x(4/3)\pi.r^3}{1.717x10^{-28}}$

$r^3 = 0.7587 \times 10^{-29}$ m^3

r =0.196 x 10^{-9} m = **0.196 nm**

2.23. $\frac{\rho_1}{\rho_2} = \frac{n_1 A_1 V_{c2} N_A}{V_{c1} N_A n_2 A_2} = \frac{n_1 V_{c2}}{n_2 V_{c1}}$

$\frac{8.87}{\rho_2} = \frac{2 x (\frac{4r}{\sqrt{3}})^3}{4x(2r\sqrt{2})^3}$

$\rho_2 = 32.573\ g/cm^3$

2.24. See Section 2.2.2.

2.25. See Section 2.2.2.

2.26. See Section 2.2.2.

2.27. See Figure 2.14**.**

2.28. See Section 2.2.5.

2.29. m_t = 100 g

P_B = 65 %

P_{lB} = 30 %

P_{sB} = 80 %

From Equations 2.4 and 2.5,

$m_l + m_s = 100$

$30\ m_l + 80\ m_s = 65 \times 100$

Solving the two equations simultaneously, we get:

m_l = mass of the alloy which is in the liquid phase = **30 g**

m_s = mass of the alloy which is in the solid phase = **70 g**

2.30. m_t = 100 g

P_B = 45 %

P_{lB} = 17 %

P_{sB} = 65 %

From Equations 2.4 and 2.5,

$m_l + m_s = 100$

$17\ m_l + 65\ m_s = 45 \times 100$

Solving the two equations simultaneously, we get:

m_l = mass of the alloy which is in the liquid phase = **41.67 g**

m_s = mass of the alloy which is in the solid phase = **58.39 g**

© 2017 Pearson Education, Inc., Hoboken, NJ. All rights reserved. This material is protected under all copyright laws as they currently exist. No portion of this material may be reproduced, in any form or by any means, without permission in writing from the publisher.

Materials for Civil and Construction Engineers 4th edition Mamlouk Solutions Manual

2.31. m_t = 100 g
P_B = 60 %
P_{lB} = 25 %
P_{sB} = 70 %
From Equations 2.4 and 2.5,
$m_l + m_s = 100$
$25\ m_l + 70\ m_s = 60 \times 100$
Solving the two equations simultaneously, we get:
m_l = mass of the alloy which is in the liquid phase = **22.22 g**
m_s = mass of the alloy which is in the solid phase = **77.78 g**

2.32. m_t = 100 g
P_B = 40 %
P_{lB} = 20 %
P_{sB} = 50 %
From Equations 2.4 and 2.5,
$m_l + m_s = 100$
$40\ m_l + 50\ m_s = 40 \times 100$
Solving the two equations simultaneously, we get:
m_l = mass of the alloy which is in the liquid phase = **33.33 g**
m_s = mass of the alloy which is in the solid phase = **66.67 g**

This Manual is protected by United States copyright laws and is provided solely for the use of instructors in teaching their courses and assessing student learning. Dissemination or sale of any part of this work (including on the World Wide Web) will destroy the integrity of the work and is not permitted.

2.33. a. Spreading salt reduces the melting temperature of ice. For example, at a salt composition of 5%, ice starts to melt at -21ºC. When temperature increases more ice will melt. At a temperature of -5ºC, all ice will melt.

b. **-21ºC**

c. **-21ºC**

2.34. See Section 2.3**.**

2.35. See Section 2**.3.**

2.36. See Section 2.4**.**

© 2017 Pearson Education, Inc., Hoboken, NJ. All rights reserved. This material is protected under all copyright laws as they currently exist. No portion of this material may be reproduced, in any form or by any means, without permission in writing from the publisher.

Materials for Civil and Construction Engineers 4th edition Mamlouk Solutions Manual