Mechanical Behavior of Materials 5th edition Dowling Solutions Manual

SKU: 9780134606545-SOLUTIONS

1.5

A plate with a width change as in Fig A.11(c) is subjected to a given force in tension and has given dimensions. It is made of a ductile polycarbonate plastic with a given yield strength. What is the safety factor against large amounts of deformation due to yielding? Does the value seem adequate?

P	w_2	w_1	ρ	t	σ_o
N	mm	mm	mm	mm	MPa
2800	24	16	4.0	6.0	62

$$S = \frac{P}{w_1 t}, \quad X_1 = \frac{\sigma_o}{S}$$

S	X_1
MPa	
29.2	**2.13**

Units for S: $N/mm^2 = MPa$

◀

The safety factor seems reasonable. Note that the quite ductile polycarbonate can deform by a large amount before failing.

© 2019 Pearson Education, Inc., Hoboken, NJ. All rights reserved. This material is protected under all copyright laws as they currently exist. No portion of this material may be reproduced, in any form or by any means, without permission in writing from the publisher.
Mechanical Behavior of Materials 5th edition Dowling Solutions Manual

1.6

A shaft with a circumferential groove as in Fig A.12(c) is subjected to a given bending moment and has given dimensions. It is made of a ductile titanium alloy with a given yield strength. What is the safety factor against large amounts of deformation due to yielding? Does the value seem adequate?

M	d_2	d_1	ρ	σ_o
N·mm	mm	mm	mm	MPa
250,000	22	18	2.0	830

$$S = \frac{32M}{\pi d_1^3}, \quad X_1 = \frac{\sigma_o}{S}$$

S	X_1
MPa	
436.6	**1.90**

Units for S: $N/mm^2 = MPa$

◀

The safety factor seems adequate. Note that the ductile titanium alloy can deform by a large amount before failing.

© 2019 Pearson Education, Inc., Hoboken, NJ. All rights reserved. This material is protected under all copyright laws as they currently exist. No portion of this material may be reproduced, in any form or by any means, without permission in writing from the publisher.
Mechanical Behavior of Materials 5th edition Dowling Solutions Manual

Answers for Problems and Questions

INSTRUCTOR'S SUPPLEMENT

The pages that follow give the answers for Problems and Questions where a numerical value or the development of a new equation is requested. Where a series of values needs to be calculated, a typical set of these is given. Approximately half of these answers are the same as those given in the textbook itself.

This supplement is not intended for distribution as a unit to students. Of course, it may be useful to provide students with answers for individual problems from this listing.

This work is protected by United States copyright laws and is provided solely for the use of instructors in teaching their courses and assessing student learning. Dissemination or sale of any part of this work (including on the World Wide Web) will destroy the integrity of the work and is not permitted.

CHAPTER 1

1.5 $X_1 = 2.13$

1.6 $X_1 = 1.90$

CHAPTER 3

3.4 **(a)** For $P = 7.22\,\text{kN}$: $\sigma = 111.7\,\text{MPa}$, $\varepsilon = 0.001652$; **(b)** $\sigma_o = 530\,\text{MPa}$; **(c)** $P_{o2} = 166.5\,\text{kN}$

3.5 **(a)** $E = 68.8\,\text{GPa}$; **(b)** $\varepsilon_p = 0.01698$; **(c)** $L_A = 150.71\,\text{mm}$, $L_0 = 150.00\,\text{mm}$; **(d)** $L_B = 153.78\,\text{mm}$, $L_0 = 152.55\,\text{mm}$

3.6 $E = 206.2\,\text{GPa}$, $\sigma_o = 831\,\text{MPa}$, $\sigma_u = 918\,\text{MPa}$, $100\varepsilon_f = 20.4\%$, $100\varepsilon_{pf} = 20.1\%$, $\%RA = 62.6\%$

3.7 $E = 71.5\,\text{GPa}$, $\sigma_o = 301\,\text{MPa}$, $\sigma_u = 323\,\text{MPa}$, $100\varepsilon_f = 14.6\%$, $100\varepsilon_{pf} = 14.3\%$, $\%RA = 56.5\%$

3.8 $E = 97.7\,\text{GPa}$, $\sigma_o = 179\,\text{MPa}$, $\sigma_u = 240\,\text{MPa}$, $100\varepsilon_f = 1.17\%$, $100\varepsilon_{pf} = 0.93\%$, $\%RA = 1.86\%$

3.9 $E = 201.3\,\text{GPa}$, $\sigma_o = 1400\,\text{MPa}$, $\sigma_u = 1492\,\text{MPa}$, $100\varepsilon_f = 9.40\%$, $100\varepsilon_{pf} = 8.86\%$, $\%RA = 38.0\%$

3.10 $E = 68.7\,\text{GPa}$, $\sigma_o = 528\,\text{MPa}$, $\sigma_u = 597\,\text{MPa}$, $100\varepsilon_f = 15.3\%$, $100\varepsilon_{pf} = 14.5\%$, $\%RA = 26.4\%$

3.11 $E = 166.1\,\text{GPa}$, $\sigma_o = 418\,\text{MPa}$, $\sigma_u = 490\,\text{MPa}$, $100\varepsilon_f = 1.154\%$, $100\varepsilon_{pf} = 0.859\%$

3.12 $E_t = 3530\,\text{MPa}$, $\sigma_{ou} = 55.9\,\text{MPa}$, $\sigma_u = 55.9\,\text{MPa}$, $100\varepsilon_f = 55.9\%$ (estimate), $100\varepsilon_{pf} = 55.0\%$, $\%RA = 60.3\%$

© 2019 Pearson Education, Inc., Hoboken, NJ. All rights reserved. This material is protected under all copyright laws as they currently exist. No portion of this material may be reproduced, in any form or by any means, without permission in writing from the publisher.
Mechanical Behavior of Materials 5th edition Dowling Solutions Manual