Reinforced Concrete Mechanics and Design 8th edition Wight Solutions Manual

SKU: 9780136834144-SOLUTIONS

3-1 What is the significance of the "critical stress"?
(a) with respect to the structure of the concrete?
(b) with respect to spiral reinforcement?
(c) with respect to strength under sustained loads?

(a) A continuous pattern of mortar cracks begins to form. As a result, there are few undamaged portions to carry load and the stress-strain curve is highly nonlinear.

(b) At the critical stress the lateral strain begins to increase rapidly. This causes the concrete core within the spiral to expand, stretching the spiral. The tension in the spiral is equilibrated by a radial compression in the core. This in turn, biaxially compresses the core, and thus strengthens it.

(c) When concrete is subjected to sustained loads greater than the critical stress, it will eventually fail.

3-2 A group of 45 tests on a given type of concrete had a mean strength of 4820 psi and a standard deviation of 550 psi. Does this concrete satisfy the strength requirement for 4000-psi concrete?

$$f_c' = f_{cr} \quad 1.34s$$
$$\text{using } f_{cr} = 4280 \text{ psi}$$
$$\text{(for design) } f_c' = 4820 \text{ psi} \quad 1.34 \quad 550 \text{ psi} = 4080 \text{ psi}$$

$$f_c' = f_{cr} \quad 2.33s + 500 \text{ psi}$$
$$\text{using } f_{cr} = 4280 \text{ psi}$$
$$\text{(for design) } f_c' = 4820 \text{ psi} \quad 2.33 \quad 550 \text{ psi} + 500 \text{ psi} = 4040 \text{ psi}$$

Because both of these exceed 4000 psi, the concrete satisfies the strength requirement for 4000 psi concrete.

3-3 The concrete containing Type I cement in a structure is cured for 3 days at 70° F followed by 6 days at 40° F. Use the maturity concept to estimate its strength as a fraction of the 28-day strength under standard curing.

Note: $°C = \frac{5}{9}(°F \quad 32)$, so 70° F = 21.1° C and 40° F = 4.4° C

$$M = \sum_{i=1}^{n} (T_i + 10° \text{ C})(t_i)$$
$$= (21.1° \text{ C} + 10° \text{ C})(3 \text{ days}) + (4.4° \text{ C} + 10° \text{ C})(6 \text{ days}) = 180° \text{ C days}$$

From Fig. 3-8 the compressive strength will be between 0.60 and 0.70 times the 28-day strength under standard curing conditions.

Reinforced Concrete Mechanics and Design 8th edition Wight Solutions Manual

3-4 Use Fig. 3-12a to estimate the compressive strength σ_2 for biaxially loaded concrete subject to: (a) $\sigma_1 = 0$. (b) $\sigma_1 = 0.50$ times the tensile strength, in tension. (c) $\sigma_1 = 0.75$ times the compressive strength, in compression.

$$\text{(a) } \sigma_2 = f_c' \text{ (b) } \sigma_2 = 0.75\, f_t' \text{ (c) } \sigma_2 = 1.4\, f_c'$$

3-5 The concrete in the core of a spiral is subjected to a uniform confining stress σ_3 of 680 psi. What will the compressive strength, σ_1 be? The unconfined uniaxial compressive strength is 5000 psi?

$$_1 = f_c' + 4.1 \quad _3 = 5000 \text{ psi} + 4.1 \quad 680 \text{ psi} = 7790 \text{ psi}$$

3-6 What factors affect the shrinkage of concrete?

(a) Relative humidity. Shrinkage increases as the relative humidity decreases, reaching a maximum at RH $\leq$ 40%.

(b) The fraction of the total volume made up of paste. As this fraction increases, shrinkage increases.

(c) The modulus of elasticity of the aggregate. As *E* increases, shrinkage decreases.

(d) The water/cement ratio. As the water content increases, the aggregate fraction decreases, causing an increase in shrinkage.

(e) The fineness of the cement. Shrinkage increases for finely ground cement that has more surface area to attract and absorb water.

(f) The effective thickness or volume to surface ratio. As this ratio increases, the shrinkage occurs more slowly, and the total shrinkage is likely reduced.

(g) Exposure to carbon dioxide tends to increase shrinkage.

3-7 What factors affect the creep of concrete?

(a) The ratio of sustained stress to the strength of the concrete. The creep coefficient, □, is roughly constant up to a stress of 0.5 f_c', but increases above that value.

(b) The humidity of the environment. The amount of creep decreases as the RH increases above 40%.

Reinforced Concrete Mechanics and Design 8th edition Wight Solutions Manual

(c) As the effective thickness or volume to surface ratio increases, the rate at which creep develops decreases.

(d) Concretes with a high paste content creep more that concretes with a large aggregate fraction because only the paste creeps.

3-8 A structure is made from concrete containing Type I cement. The average ambient relative humidity is 70 percent. The concrete was moist-cured for 7 days. f_c' = 4000 psi.

(a) Compute the unrestrained shrinkage strain of a rectangular beam with cross-sectional dimensions 8 in. × 20 in. at 2 years after the concrete was placed.

(b) Compute the axial shortening of a 20 in. × 20 in. × 12 ft plain concrete column at age 3 years. A compression load of 400 kips was applied to the column at age 28 days.

(a)
Compute the humidity modification factor.

$$_{rh} = 1.40 \quad 0.01 \quad RH = 1.40 \quad 0.01 \quad 70\% = 0.70$$

Compute the volume/surface area ratio modification factor.

$$\text{Volume per foot of beam} = 12 \text{ in.} \quad 8 \text{ in.} \quad 20 \text{ in.} = 1920 \text{ in.}^3$$

$$\text{Surface area per foot of beam} = 2 \quad [(12 \text{ in.} \quad 8 \text{ in.}) + (12 \text{ in.} \quad 20 \text{ in.})] = 672 \text{ in.}^2$$

$$_{vs} = 1.2 \quad ^{0.12V/S} = 1.2 \quad ^{0.12 \quad 1920 \text{ in.}^3/672 \text{ in.}^2} \quad 0.94$$

Compute the ultimate shrinkage strain:

$$(\ _{sh})_u = \ _{rh} \quad _{vs} \quad 780 \quad 10^{\ 6} = 0.70 \quad 0.94 \quad 780 \quad 10^{\ 6} = 513 \quad 10^{\ 6}$$

Compute the shrinkage strain after 2 years:

$$t = 2 \text{ yr} \quad \frac{365 \text{ days}}{\text{yr}} \quad 7 \text{ days} = 723 \text{ days}$$

$$(\ _{sh})_t = \frac{t}{35 \text{ days} + t}(\ _{sh})_u = \frac{723 \text{ days}}{35 \text{ days} + 723 \text{ days}} 513 \quad 10^{\ 6} \quad 490 \quad 10^{\ 6}$$

(b)
Compute the ultimate shrinkage strain coefficient, C_u.

$$_{rh} = 1.27 \quad 0.0067 \quad RH = 1.27 \quad 0.0067 \quad 70\% = 0.80$$

$$_{to} = 1.25 \quad t_o^{\ 0.118} = 1.25 \quad (28 \text{ days})^{\ 0.118} = 0.84$$

$$_{vs} = 0.67(1 + 1.13^{\ 0.54V/S})$$

$$\text{Where } V = 20 \text{ in.} \quad 20 \text{ in.} \quad 12 \text{ ft} \quad 12 \text{ in./ ft} = 57{,}600 \text{ in.}^3$$

$$S = 4 \text{ sides} \quad 20 \text{ in.} \quad 12 \text{ ft} \quad 12 \text{ in./ ft} = 11{,}500 \text{ in.}^2$$

$$_{vs} = 0.67(1 + 1.13^{\ 0.54 \quad 57{,}600 \text{ in.}^3/11{,}500 \text{ in.}^2}) = 1.15$$

$$C_u = 2.35 \quad _{rh} \quad _{to} \quad _{vs} = 2.35 \quad 0.80 \quad 0.84 \quad 1.15 = 1.82$$

Compute the creep coefficient for the time since loading, C_t.

Reinforced Concrete Mechanics and Design 8th edition Wight Solutions Manual

$$t = 3 \text{ yr} \quad \frac{365 \text{ days}}{\text{yr}} \quad 28 \text{ days} = 1067 \text{ days}$$

$$C_t = \frac{t^{0.6}}{10 \text{ days} + t^{0.6}} C_u = \frac{(1067 \text{ days})^{0.6}}{10 \text{ days} + (1067 \text{ days})^{0.6}} \quad 1.82 \quad 1.58$$

Compute the total stress-dependent strain, ε_c (total).

First, calculate the creep strain since the load was applied:

$$f_{cm} = 1.2 f_c' = 1.2 \quad 4000 \text{ psi} = 4800 \text{ psi}$$

$$E_c(28 \text{ days}) = 57{,}000\sqrt{4800 \text{ psi}} = 3.95 \quad 10^6 \text{ psi}$$

$$_{cc}(t, t_o) = \frac{_c(t_o)}{E_c(28 \text{ days})} \quad C_t = \frac{400{,}000 \text{ lb}/(20 \text{ in.} \quad 20 \text{ in.})}{3.95 \quad 10^6 \text{ psi}} \quad 1.58 = 0.4 \quad 10^{-3}$$

Then, calculate the initial strain when the load is applied:

$$f_c'(t_o) = f_c'(28 \text{ days}) = 4000 \text{ psi}$$

$$f_{cm}(t_o) = 1.2 f_c'(t_o) = 1.2 \quad 4000 \text{ psi} = 4800 \text{ psi}$$

$$E_c(t_o) = 57{,}000\sqrt{f_{cm}(t_o)} = 57{,}000\sqrt{4800 \text{ psi}} = 3.95 \quad 10^6 \text{ psi}$$

$$_c(t_o) = \frac{_c(t_o)}{E_c(t_o)} = \frac{400{,}000 \text{ lb}/(20 \text{ in.} \quad 20 \text{ in.})}{3.95 \quad 10^6 \text{ psi}} = 0.253 \quad 10^{-3}$$

$$_c(\text{total}) = \ _c(t_o) + \ _{cc}(t, t_o) = 0.253 \quad 10^{-3} + 0.4 \quad 10^{-3} = 0.653 \quad 10^{-3}$$

Compute the axial shortening

The column is 12 ft long, so the total expected shortening due to stress-dependent strain is,

$$\ell = \ell \times \ _c(\text{total}) = 144 \text{ in.} \times 0.653 \times 10^{-3} = 0.094 \text{ in.}$$

Reinforced Concrete Mechanics and Design 8th edition Wight Solutions Manual